

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 6,857,461 B2
DATED : February 22, 2005
INVENTOR(S) : Dieter Girlich & Juergen Schaedlich-Stubenrauch

Page 1 of 4

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

The title page, should be deleted and substitute therefor the attached title page as shown on the attached pages.

Delete drawing sheets 1-2, and substitute therefore the drawing sheets, consisting of Figs 1-8, as shown on the attached pages

Signed and Sealed this

Twelfth Day of July, 2005

A handwritten signature in black ink, appearing to read "Jon W. Dudas". The signature is stylized with a large, looping initial "J" and a distinct "D" at the end.

JON W. DUDAS
Director of the United States Patent and Trademark Office

(12) **United States Patent**
Girlich et al.

(10) **Patent No.:** **US 6,857,461 B2**
(45) Date of Patent: **Feb. 22, 2005**

(54) **METHOD AND DEVICE FOR THE
 PRODUCTION OF RETICULAR
 STRUCTURES**

3,946,039 A * 3/1976 Walz 264/628
 3,996,991 A * 12/1976 Ugata et al. 164/35

(76) **Inventors:** Dieter Girlich, Tzschimmerstr. 32,
 D-01309 Dresden (DE); Juergen
 Schaedlich-Stubenrauch,
 Vaalserhaagweg 4, NL-6291 Vaals (NL)

FOREIGN PATENT DOCUMENTS

JP 63-84758 * 4/1988 B22D/19/00

* cited by examiner

(*) **Notice:** Subject to any disclaimer, the term of this
 patent is extended or adjusted under 35
 U.S.C. 154(b) by 126 days.

Primary Examiner—M. Alexandra Elve

Assistant Examiner—Kevin P. Kerns

(74) Attorney, Agent, or Firm—Patricia M. Mathers;
 Thomas L. Bohan

(21) **Appl. No.:** 10/079,331

(22) **Filed:** Feb. 20, 2002

(65) **Prior Publication Data**

US 2002/0088598 A1 Jul. 11, 2002

Related U.S. Application Data

(63) **Continuation of application No. PCT/DE00/02597, filed on**
 Aug. 4, 2000.

(30) **Foreign Application Priority Data**

Aug. 20, 1999 (DE) 199 39 155

(51) **Int. Cl.**⁷ B22C 9/04

(52) **U.S. Cl.** 164/34; 164/35; 164/45

(58) **Field of Search** 164/34, 35, 45,
 164/235, 246

(56) **References Cited**


U.S. PATENT DOCUMENTS

3 616 841 A 11/1971 Walz

(57) **ABSTRACT**

A method of producing reticular structures, particularly
 metallic reticular structures, as well as a device suitable for
 the production thereof. The method and device enable
 continuous and/or automated production of such structures,
 and particularly, large-scale automated production of large-
 dimensioned reticular structures. A reticulated foam pre-
 structure is placed into a first container and infiltrated with
 a refractory material. After solidification, the mold formed
 by the refractory material is removed from the first container
 and the foam pre-structure stripped from the mold. The mold
 is then pre-heated and placed into a second container and
 infiltrated with a molten substance that forms the reticular
 structure when solidified. The filled mold may be covered
 with a solid jacket as a means of controlling the rate and
 progression of solidification of the molten substance to form
 a fine-grained, bubble-free structure.

10 Claims, 2 Drawing Sheets



U.S. Patent

Feb. 22, 2005

Sheet 1 of 2

6,857,461 B2




FIG. 1




FIG. 2




FIG. 3




FIG. 4

U.S. Patent

Feb. 22, 2005

Sheet 2 of 2

6,857,461 B2




FIG. 5




FIG. 6




FIG. 7




FIG. 8